For Mailing Attach Postage Stamp

## Gloss Interior Enamel Finish

There is a B. P. S. finish for every purpose paint -enamel-stain - varnish ~ B. P. S. products are built to quality only -each finish must be the best of its kind



34 Market Street
Somersworth, N. H.
Picture framing Glass & Seeds
B. P. S. Paints & Varnishes



## Gloss Interior Enamel Finish

### Combines Beauty and Perfect Service

FOR interior enamel finishing where a beautiful - durable - washable - high gloss'- easy to apply enamel finish is desired.

We all wish our surroundings to be beautiful and sanitary, but owing to the fact that most enamel finishes have a tendency to "work hard," many folks have heretofore used an ordinary paint for their interior painting.

In B. B. S. Gloss Interior Enamel Finish we offer an easy working product that can be applied with the same effort and time as ordinary paint - but the results obtained are so superior that this finish is placed in a class by itself. Our complete directions,



Also No. 9 WHITE



given in this folder, enable you to approach "the work in hand" with confidence and assurance that your "finished work" will be beautiful - sanitary - washable and satisfactory.

Recommended for kitchen walls and ceilings, bathrooms, woodwork, lavatories, cupboards, furniture, radiators, brick and plaster work, metal ceilings - in fact, its use for inside finishing is almost universal.

Can be washed repeatedly with soap and water without injury to the finish, thereby keeping it in a wholesome and sanitary condition.

#### No. 9 WHITE

B.P.S. Gloss Interior Enamel Finish No. 9
White is known as the "White that stays
White." Will not turn yellow from
repeated washings with soap and water - a
beautiful - easy to apply - snow white
enamel finish that retains its beauty indefinitely.

Covering Capacity - One Coat - About 550 sq. feet to the gallon. Two Coats - About 300 sq. feet to the gallon.

#### **DIRECTIONS FOR USE**

#### **SHADES**

Stir B. P. S. Gloss Interior Ename! Finish thoroly - pour it back and forth from can to can.

See that the surface to be painted is dry and free from greasy substances, dirt and all loose paint. The temperature should be between 60 and 80 degrees.

OLD WORK - Apply one or two coats of B. P. S. Gloss Interior Enamel Finish, depending on the surface to be painted. One Coat Work - Applyjustas it comes in the can. Two Coat Work - First Coat - Reduce with one pint of turpentine to the gallon. Second Coat - Apply as it comes in the can.

NEW WORK - On wood, plaster, composition board, metal, etc. Two Coat Work - First or Priming Coat - Reduce with one quart of pure raw linseed oil to the Second or Finishing Coat gallon. Apply as it comes in the can. Three Coat Work - First or Priming Coat - Reduce with one-half gallon of pure raw linseed oil to the gallon. Second Coat - Reduce with one pint of turpentine to the gallon. Third or Finishing Coat - Apply as it comes in the can. Allow at least 36 hours between coats. If the B.P.S. Gloss Interior Enamel Finish is too heavy to brush freely reduce with a small amount of turpentine. If extra fine work is desired, sandpaper first coat lightly.

#### **DIRECTIONS FOR USE**

#### WHITE

Stir B. P. S. Gloss Interior Enamel Finish White thoroly - pour it back and forth from can to can.

See that the surface to be painted is dry and free from greasy substances, dirt and all loose paint. The temperature should be between 60 and 80 degrees.

oLD WORK - Apply one or two coats of B. P. S. Gloss Interior Enamel Finish White, depending on the surface to be painted. One Coat Work - Apply just as it comes in the can. Two Coat Work - First Coat - Reduce with one pint of turpentine to the gallon. Second Coat - Apply as it comes in the can.

NEW WORK - On wood, plaster, composition board, metal, etc. Two Coat Work - First or Priming Coat - Apply B. P.S. Flat White reduced with one quart of pure raw linseed oil to the gallon of paint. Finishing Coat - Apply B. P. S. Gloss Interior Enamel Finish White just as it comes in the can. Three Coat Work - Priming Coat - Same as on two coat work. Second Coat - Apply B.P.S. Flat White reduced with one pint of turpentine to the gallon. Finishing Coat - Apply B. P. S. Gloss Interior Enamel Finish White as it comes in the can. Allow at least 36 hours between coats. If the Enamel Finish is too heavy to spread freely, add a small amount of turpentine - do not use linseed oil. If extra fine work is desired, sandpaper first coat lightly.



# GLOSS INTERIOR ENAMEL FINISH



For Interior Woodwork, Furniture, Etc.

The Patterson-Sargent Co.
CLEVELAND CHICAGO NEW YORK
KANSAS CITY ST. PAUL DETROIT
LONG ISLAND CITY BOSTON
SIOUX CITY FORT WORTH



